

CORRECTED VERSION

(19) World Intellectual Property Organization
International Bureau(43) International Publication Date
9 November 2000 (09.11.2000)

PCT

(10) International Publication Number
WO 00/66506 A1(51) International Patent Classification⁷: C03C 17/22.
17/34, 23/00IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU,
LV, MA, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT,
RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA,
UG, US, UZ, VN, YU, ZA, ZW.

(21) International Application Number: PCT/US00/11711

(22) International Filing Date: 1 May 2000 (01.05.2000)

(25) Filing Language: English

(26) Publication Language: English

(84) Designated States (*regional*): ARIPO patent (GH, GM,
KE, LS, MW, SD, SL, SZ, TZ, UG, ZW), Eurasian patent
(AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent
(AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU,
MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM,
GA, GN, GW, ML, MR, NE, SN, TD, TG).(30) Priority Data:
09/303,548 3 May 1999 (03.05.1999) US

Published:

— with international search report
— with amended claims(71) Applicant: GUARDIAN INDUSTRIES CORPORA-
TION [US/US]; 2300 Harmon Road, Auburn Hills, MI
48326-1714 (US).

Date of publication of the amended claims: 25 January 2001

(72) Inventor: VEERASAMY, Vijayen, S.; 22575 Maywood
Court, Farmington Hills, MI 48335 (US).(48) Date of publication of this corrected version:
21 February 2002(74) Agent: RHOA, Joseph, A.; Nixon & Vanderhye P.C.,
1100 North Glebe Road, Suite 800, Arlington, VA 22201-
4714 (US).(15) Information about Correction:
see PCT Gazette No. 08/2002 of 21 February 2002, Section
II(81) Designated States (*national*): AE, AL, AM, AT, AU, AZ,
BA, BB, BG, BR, BY, CA, CH, CN, CR, CU, CZ, DE, DK,
DM, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL,For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.

(54) Title: HIGHLY TETRAHEDRAL AMORPHOUS CARBON COATING ON GLASS

(57) Abstract: A soda inclusive glass substrate is coated with a highly tetrahedral amorphous carbon inclusive layer that is a form of diamond-like carbon (DLC). In certain embodiments, the amorphous carbon layer includes at least about 35 % sp³ carbon-carbon bonds, more preferably at least about 70 %, and most preferably at least about 80 % of the sp³ carbon-carbon bonds. The high density (e.g. greater than or equal to about 2.4 gm/cm³) of the amorphous carbon layer prevents soda from exiting the glass and reacting with water at surface(s) of the glass, thereby minimizing visible stains or (corrosion) on the glass. The high density amorphous carbon layer also may repel water. In some embodiments, the highly tetrahedral amorphous carbon layer is part of a larger DLC coating, while in other embodiments the highly tetrahedral layer forms the entirety of a DLC coating on the substrate.

WO 00/66506 A1

HIGHLY TETRAHEDRAL
AMORPHOUS CARBON COATING ON GLASS

This invention relates to a diamond-like carbon (DLC) coating provided on (directly or indirectly) a glass or other substrate. More particularly, in certain preferred embodiments, this invention relates to a highly tetrahedral amorphous diamond like carbon coating on a soda inclusive glass substrate (e.g. on a soda lime silica glass substrate) for purposes of repelling water and/or reducing corrosion on the coated article. Ion beam and filtered carbon cathodic arc deposition are preferred methods of deposition for the coating.

BACKGROUND OF THE INVENTION

Soda inclusive glasses are known in the art. For example, see U.S. Patent No. 5,214,008, which is hereby incorporated herein by reference.

Soda lime silica glass, for example, is used for architectural glass, automotive windshields, and the like. The aforesaid '008 patent discloses one type of soda lime silica glass known in the art.

Unfortunately, conventional soda inclusive glasses are susceptible to environmental corrosion which occurs when sodium (Na) diffuses from or leaves the glass interior. This sodium, upon reaching the surface of the glass, may
5 react with water to produce visible stains or smears (e.g. stains of sodium hydroxide) on the glass surface. Such glasses are also susceptible to retaining water on their surfaces in many different environments, including when used as automotive windows (e.g. backlites, side windows, and/or
10 windshields). These glasses are also susceptible to fogging up on the interior surface thereof in automotive and other environments.

In view of the above, it is apparent that there exists a need in the art to prevent and/or minimize visible
15 stains/corrosion on soda inclusive coated glass surfaces. There also exists a need in the art to provide a strong protective coating on window substrates. Other needs in the art include the need for a coating on glass that reduces the coated article's susceptibility to fogging up in automotive
20 and other environments, and the need for a coated glass article that can repel water and/or dirt.

It is known to provide diamond like carbon (DLC) coatings on glass. U.S. Patent No. 5,637,353, for example, states that DLC may be applied on glass. The '353 patent teaches that because there is a bonding problem between
5 glass and that type of DLC, an intermediate layer is provided therebetween. Moreover, the '353 patent does not disclose or mention the highly tetrahedral amorphous type of DLC used in many embodiments set forth below. The DLC of the '353 patent would not be an efficient corrosion
10 minimizer on glass in many instances due to its low density (likely less than 2.0 gm/cm³). Still further, the DLC of the '353 patent is deposited in a less than efficient manner for certain embodiments of this invention.

It is known that many glass substrates have small
15 cracks defined in their surface. The stress needed to crack glass typically decreases with increasing exposure to water. When water enters such a crack, it causes interatomic bonds at the tip of the crack to rupture. This weakens glass. Water can accelerate the rate of crack growth more than a
20 thousand times by attacking the structure of the glass at the root or tip of the crack. Strength of glass is in part controlled by the growth of cracks that penetrate the glass.

Water, in these cracks, reacts with glass and causes it to crack more easily as described in "The Fracturing of Glass," by T.A. Michalske and Bruce C. Bunker, hereby incorporated herein by reference. Water molecules cause a concerted
5 chemical reaction in which a silicon-oxygen bond (of the glass) at the crack tip and on oxygen-hydrogen bond in the water molecule are both cleaved, producing two silanol groups. The length of the crack thus increases by one bond rupture, thereby weakening the glass. Reaction with water
10 lowers the energy needed to break the silicon-oxygen bonds by a factor of about 20, and so the bond-rupture allows glass cracks to grow faster.

Thus, there also exists a need in the art for preventing water from reaching silicon-oxygen bonds at tips
15 of cracks in a glass substrate, so as to strengthen the glass.

It is a purpose of different embodiments of this invention to fulfill any or all of the above described needs in the art, and/or other needs which will become apparent to
20 the skilled artisan once given the following disclosure.

SUMMARY OF THE INVENTION

An object of this invention is to provide a coated article that can shed water (e.g. automotive windshield, automotive backlite, automotive side window, architectural window, etc.).
5 window, etc.)

Another object of this invention is to provide a system or means for reducing or minimizing corrosion on soda inclusive coated glass articles.

Another object of this invention is to provide a coated glass article wherein a DLC coating protects the glass from acids such as HF, nitric, and sodium hydroxide (the coating may be chemically inert).
10 glass article wherein a DLC coating protects the glass from acids such as HF, nitric, and sodium hydroxide (the coating may be chemically inert).

Another object of this invention is to provide a coated glass article that is not readily susceptible to fogging up.

Another object is to provide a barrier layer with no pin holes on a glass substrate.
15 Another object is to provide a barrier layer with no pin holes on a glass substrate.

Another object of this invention is to provide a coated glass article that is abrasion resistant, and/or can repel dirt and the like.

Another object of this invention is to provide a glass substrate with a DLC coating inclusive of a highly
20 Another object of this invention is to provide a glass substrate with a DLC coating inclusive of a highly

tetrahedral dense amorphous carbon layer, either in direct or indirect contact with the substrate.

Another object of this invention is to provide a DLC coating on a substrate, wherein the coating includes different portions or layers with different densities and different sp^3 carbon-carbon bond percentages. The ratio of sp^3 to sp^2 carbon-carbon bonds may be different in different layers or portions of the coating. Such a coating with varying compositions therein may be continuously formed by varying the ion energy used in the deposition process so that stresses in the coating are reduced in the interfacial portion/layer of the DLC coating immediately adjacent the underlying substrate. Thus, a DLC coating may have therein an interfacial layer with a given density and sp^3 carbon-carbon bond percentage, and another layer with a higher density and higher sp^3 carbon-carbon bond percentage.

Generally speaking, this invention fulfills certain of the above described needs/objects in the art by providing a coated glass comprising:

a glass substrate including at least about 5% by weight soda/ Na_2O ;

an amorphous carbon layer provided on the glass substrate in order to reduce corrosion or stains on the coated glass, wherein said amorphous carbon layer includes sp^2 and sp^3 carbon-carbon bonds; and

5 wherein the amorphous carbon layer has more sp^3 carbon-carbon bonds than sp^2 carbon-carbon bonds.

In other embodiments, this invention fulfills certain of the above described needs in the art by providing a coated glass comprising:

10 a soda inclusive glass substrate comprising, on a weight basis, from about 60-80% SiO_2 , from about 10-20% Na_2O , from about 0-16% CaO , from about 0-10% K_2O , from about 0-10% MgO , and from about 0-5% Al_2O_3 ; and

15 a non-crystalline diamond-like carbon (DLC) coating provided on the glass substrate, wherein the DLC coating includes at least one highly tetrahedral amorphous carbon layer having at least about 35% sp^3 carbon-carbon bonds.

In certain embodiments, the glass substrate is a soda lime silica float glass substrate.

20 In preferred embodiments, the entire DLC coating or alternatively only a layer within the DLC coating, has a

density of from about 2.4 to 3.4 gm/cm³, most preferably from about 2.7 to 3.0 gm/cm³.

In certain embodiments, the tetrahedral amorphous carbon layer has the aforesaid density range and includes at least about 70% sp³ carbon-carbon bonds, and most preferably at least about 80% sp³ carbon-carbon bonds.

In certain embodiments, the DLC coating includes a top layer (e.g. from about 2 to 8 atomic layers, or less than about 20 Å) that is less dense than other portions of the DLC coating, thereby providing a solid lubricant portion at the top surface of the DLC coating. Layered graphene connected carbon atoms are provided in this thin layer portion. The coefficient of friction is less than about 0.1 for this thin layer portion.

Another advantage of this invention is that the temperature of the glass substrate is less than about 200° C., preferably less than about 150° C., most preferably from about 60-80° C., during the deposition of DLC material. This is to minimize graphitization during the deposition process.

This invention further fulfills the above described needs in the art by providing a window having a substrate

and a highly tetrahedral amorphous carbon layer thereon,
wherein the substrate is or includes at least one of
borosilicate glass, soda lime silica glass, and plastic.

This invention will now be described with respect to
5 certain embodiments thereof, along with reference to the
accompanying illustrations.

IN THE DRAWINGS

Figure 1 is a side cross sectional view of a coated
article according to an embodiment of this invention,
10 wherein a substrate is provided with a DLC coating including
at least two layers therein.

Figure 2 is a side cross sectional view of a coated
article according to another embodiment of this invention,
wherein a highly tetrahedral amorphous carbon DLC coating is
15 provided on and in contact with a substrate.

Figure 3 is a side cross sectional view of a coated
article according to yet another embodiment of this
invention wherein a low-E or other coating is provided on a
substrate, with the DLC coating of either of the Fig. 1 or
20 Fig. 2 embodiments also on the substrate but over top of the
intermediate low-E or other coating.




Figure 4 illustrates an exemplar sp^3 carbon atom hybridization bond.

Figure 5 illustrates an exemplar sp^2 carbon atom hybridization bond.

5 Figure 6 illustrates exemplar sp hybridizations of a
carbon atom.

Figure 7 is a side cross sectional view of carbon ions penetrating the substrate or DLC surface so as to strongly bond a DLC layer according to any embodiment herein.

10 Figure 8 is a side cross sectional view of a coated glass substrate according to an embodiment of this invention, illustrating DLC bonds penetrating cracks in the surface of a glass substrate.

15 DETAILED DESCRIPTION OF
CERTAIN EMBODIMENTS OF THIS INVENTION

Referring now more particularly to the accompanying drawings in which like reference numerals indicate like elements throughout the accompanying views.

Figure 1 is a side cross sectional view of a coated
20 glass article according to an embodiment of this invention,
wherein at least one diamond-like carbon (DLC) protective

coating(s) 3 is provided directly on soda-inclusive glass substrate 1. DLC coating 3 in the Fig. 1 embodiment includes at least one highly tetrahedral amorphous carbon (ta-C) layer 7 that has a high density (e.g. greater than about 2.4 grams per cubic centimeter) and functions to repel water and seal soda within the soda inclusive glass substrate. Coating 3 further includes at least one interfacing layer 8 directly adjacent substrate 1, where layer 8 has a lesser density and a lesser percentage of sp³ carbon-carbon bonds than ta-C layer 7. Even though layer 8 differs from layer 7 in these manner(s), interfacing layer 8 may or may not qualify as ta-C with a density of at least about 2.4 gm/cm³, as described below. It is noted that in certain embodiments, coating 3 may include multiple ta-C layers 7 and/or multiple layers 8. Layers 7 and 8 of the coating may be formed in a continuous or non-continuous deposition process in different embodiments of this invention.

Figure 2 is a side cross sectional view of a coated glass article according to another embodiment of this invention, wherein at least one DLC coating(s) 3 is provided on glass substrate 1. In the Fig. 2 embodiment,

substantially the entire DLC coating 3 is made up of highly tetrahedral amorphous carbon (ta-C), similar to layer 7, ~~having a density of at least about 2.4 grams per cubic~~ centimeter and a high percentage (e.g. at least about 35%,
5 more preferably at least about 70%, and most preferably at least about 80%) of sp^3 carbon-carbon bonds. In other words, ta-C layer 7 from the Fig. 1 embodiment forms the entirety of DLC coating 3 in the Fig. 2 embodiment. DLC coating 3 in the Fig. 2 embodiment may or may not have equal
10 densities and/or the same percentages of sp^3 carbon-carbon bonds throughout the thickness of coating 3, as these parameters may be varied throughout layers 3, 7 and 8 in the Fig. 1 and 2 embodiments by changing the ion energy used during the deposition process of coating 3.

15 In the Fig. 3 embodiment, a low-E or other coating 5 is provided between substrate 1 and DLC coating 3 (i.e. the DLC coating of either the Fig. 1 or Fig. 2 embodiment).

However, DLC coating 3 is still on substrate 1 in the Fig. 3 embodiment, along with a ta-C portion 7 of coating 3. Thus,
20 the term "on" herein means that substrate 1 supports DLC coating 3 or any layer (e.g. 7, 8) thereof, regardless of whether or not other layer(s) 5 are provided therebetween.

Thus, protective coating 3 may be provided directly on substrate 1 as shown in Figs. 1-2, or may be provided on substrate 1 with a low-E or other coating(s) 5 therebetween as shown in Fig. 3. Coating 5, instead of its illustrated position in Fig. 3, may also be provided on top of DLC coating 3 so that coating 3 (of either the Fig. 1 or Fig. 2 embodiment) is located between coating(s) 5 and substrate 1. In still other embodiments, a DLC coating 3 may be provided on both sides of a low-E coating 5.

10 Exemplar coatings (in full or any portion of these coatings) that may be used as low-E or other coating(s) 5, either on top of or below DLC coating 3, are shown and/or described in any of U.S. Patent Nos. 5,837,108, 5,800,933, 5,770,321, 5,557,462, 5,514,476, 5,425,861, 5,344,718, 15 5,376,455, 5,298,048, 5,242,560, 5,229,194, 5,188,887 and 4,960,645, which are all hereby incorporated herein by reference. Simple silicon oxide and/or silicon nitride coating(s) may also be used as coating(s) 5.

As will be discussed in more detail below, highly tetrahedral amorphous carbon (ta-C) layer(s) 7 is a special form of diamond-like carbon (DLC), and includes at least about 35% sp³ carbon-carbon bonds (i.e. it is highly

tetrahedral). In certain embodiments of this invention, ta-C layer(s) 7 has at least about 35% sp^3 carbon-carbon bonds of the total sp bonds in the layer, more preferably at least about 70%, and most preferably at least about 80% sp^3 carbon-carbon bonds so as to increase the density of layer 7 and its bonding strength. The amounts of sp^3 bonds may be measured using Raman finger-printing and/or electron energy loss spectroscopy. The high amount of sp^3 bonds increases the density of layer thereby allowing it to prevent soda diffusion to the surface of the coated article.

Ta-C layer 7 forms the entirety of DLC coating 3 in the Fig. 2 embodiment, and ta-C layer 7 forms only a portion of DLC coating 3 in the Fig. 1 embodiment. This is because interfacial amorphous carbon layer 8 in the Fig. 1 embodiment sometimes has a density less than about 2.4 grams per cubic centimeter and/or less than about 35% sp^3 carbon-carbon bonds. However, it is noted that DLC coating 3 has an interfacial layer immediately adjacent substrate 1 in each of the Fig. 1 and Fig. 2 embodiments, with the difference being that the interfacial layer in the Fig. 2 embodiment has a density of at least about 2.4 grams per cubic centimeter and at least about 35% sp^3 (more preferably

at least about 70%, and most preferably at least about 80%) carbon-carbon bonds. Thus, layer 7 herein refers to both layer 7 as illustrated in the Fig. 1 embodiment as well as DLC coating 3 in the Fig. 2 embodiment.

5 At least some carbon atoms of DLC coating 3, and/or some sp^2 and/or sp^3 carbon-carbon bonds, are provided in fissures or cracks in a surface (e.g. top surface) of the glass substrate, or may penetrate the glass surface of substrate 1 itself or the surface of growing DLC, so as to
10 strongly bond coating 3 to substrate 1. Subimplantation of carbon atoms into the surface of substrate 1 enables coating 3 to be strongly bonded to substrate 1.

For purposes of simplicity, Figure 4 illustrates an exemplar sp^3 carbon-carbon or C-C bond (i.e. carbon to
15 carbon diamond like bond) in coating 3, Figure 4 an exemplar sp^2 C-C bond in coating 3, and Figure 5 an exemplar sp .

The provision of dense (density of at least about 2.4 gm/cm³) ta-C layer 7 on soda inclusive glass substrate 1 reduces the amount of soda which can exit the substrate or
20 reach the surface of the substrate or coated article (i.e. ta-C limits sodium diffusion from the substrate). Thus, less soda is allowed to react with water or other

material(s) on the surface of the article. The end result is that the provision of ta-C layer 7 on the substrate ~~reduces stains and/or corrosion on the glass article~~ which can form over time. The large number of sp^3 carbon-carbon bonds increases the density of layer 7 and allows the layer to repel water and minimize soda diffusion from soda inclusive glass.

Coating(s) 3, and layer(s) 7, 8, also strengthen the glass article, reduce stress at the bonding surfaces between coating 3 and substrate 1, and provide a solid lubricant surface on the article when coating 3 is located at a surface of the article. Coating(s) 3 and/or layer 7 may include a top layer portion (e.g. the top 3 to 15 Å) that is less dense than central areas of coating 3, thereby providing a solid lubricant at the top surface of coating 3 furthest from the substrate so that the article is resistant to scratching. Ta-C layer 7 also provides resistance to water/moisture entering or coming into substrate 1. Coating 3, and thus ta-C layer 7, are preferably formed/deposited continuously across glass substrate 1, absent any pinholes or apertures.

In certain embodiments, layer 7 and/or 8 adjacent the glass substrate is deposited at an ion energy that allows significant numbers of carbon atoms to penetrate cracks in the glass surface as shown in Figure 8. The small size of
5 carbon atoms and the ion energy utilized prevent substantial water from reaching the tip of the crack(s). This strengthens the glass in the long term by slowing down and/or stopping the rupture of silicon-oxygen bonds at crack tips caused by water exposure.

10 Advantages associated with certain embodiments of this invention include: (i) coated window articles that can shed water in different environments (e.g. automotive windows such as backlites and windshields, or commercial and residential windows); (ii) anti-fog coated articles that are
15 resistant to fogging up; (iii) strengthened coated windows; (iv) abrasion resistant coated windows; (v) coated articles that can repel dirt; and (vi) coated glass articles less
20 susceptible to visible corrosion on surfaces thereof. For example, in automotive window embodiments, the outer surface of substrate 1 exposed to the environment is coated with coating 3 in accordance with any of the Fig. 1-3 embodiments. In anti-fog automotive embodiments, the inner

surface of automotive window substrates 1 may be coated with coating 3 in accordance with any of the Fig. 1-3 embodiments.

In certain embodiments, coating 3 is at least about 70% transparent to or transmissive of visible light rays, preferably at least about 80%, and most preferably at least about 90% transparent to visible light rays.

In certain embodiments, DLC coating 3 (and thus layer 7 in the Fig. 2 embodiment) may be from about 30 to 3,000 Å thick, most preferably from about 50 to 300 Å thick. As for glass substrate 1, it may be from about 1.5 to 5.0 mm thick, preferably from about 2.3 to 4.8 mm thick, and most preferably from about 3.7 to 4.8 mm thick. Ta-C layer 7, in certain embodiments, has a density of at least about 2.4 grams per cubic centimeter, more preferably from about 2.4 to 3.4 gm/cm³, and most preferably from about 2.7 to 3.0 gm/cm³.

Substrate 1 includes soda or Na₂O in certain embodiments of this invention. Thus, ta-C layer(s) 7 minimize the amount of soda that can reach the surface of the coated article and cause stains/corrosion. In certain embodiments, substrate 1 includes, on a weight basis, from

about 60-80% SiO_2 , from about 10-20% Na_2O , from about 0-16% CaO , from about 0-10% K_2O , from about 0-10% MgO , and from about 0-5% Al_2O_3 . In certain other embodiments, substrate 1 may be soda lime silica glass including, on a weight basis,

5 from about 66-75% SiO_2 , from about 10-20% Na_2O , from about 5-15% CaO , from about 0-5% MgO , from about 0-5% Al_2O_3 , and from about 0-5% K_2O . Most preferably, substrate 1 is soda lime silica glass including, by weight, from about 70-74% SiO_2 , from about 12-16% Na_2O , from about 7-12% CaO , from

10 about 3.5 to 4.5% MgO , from about 0 to 2.0% Al_2O_3 , from about 0-5% K_2O , and from about 0.08 to 0.15% iron oxide.

Soda lime silica glass according to any of the above embodiments may have a density of from about 150 to 160 pounds per cubic foot (preferably about 156), an average

15 short term bending strength of from about 6,500 to 7,500 psi (preferably about 7,000 psi), a specific heat (0-100 degrees C) of about 0.20 Btu/lbF, a softening point of from about 1330 to 1345 degrees F, a thermal conductivity of from about 0.52 to 0.57 Btu/hrftF, and a coefficient of linear

20 expansion (room temperature to 350 degrees C) of from about 4.7 to 5.0×10^{-6} degrees F. In certain embodiments, any glass disclosed in U.S. Patent No. 5,214,008 or Patent No.

5,877,103, each incorporated herein by reference, may be used as substrate 1. Also, soda lime silica float glass available from Guardian Industries Corp., Auburn Hills, Michigan, may be used as substrate 1.

5 Any such aforesaid glass substrate 1 may be, for example, green, blue or grey in color when appropriate colorant(s) are provided in the glass.

 In certain other embodiments of this invention, substrate 1 may be of borosilicate glass, or of
10 substantially transparent plastic. In certain borosilicate embodiments, the substrate 1 may include from about 75-85% SiO_2 , from about 0-5% Na_2O , from about 0 to 4% Al_2O_3 , from about 0-5% K_2O , from about 8-15% B_2O_3 , and from about 0-5% Li_2O .

15 In still further embodiments, an automotive window (e.g. windshield or side window) including any of the above glass substrates laminated to a plastic substrate may combine to make up substrate 1, with the coating 3 of any of the Figs. 1-3 embodiments provided on either or both sides
20 of such a window. Other embodiments would have substrate 1 made up of a sheet of soda lime silica glass laminated to a plastic sheet for automotive window purpose, with coating(s)

3 of any of the Fig. 1-3 embodiments on the inner side of the substrate bonded to the plastic. In other embodiments, substrate 1 may include first and second glass sheets of any of the above mentioned glass materials laminated to one another, for use in window (e.g. automotive windshield, residential window, commercial window, automotive side window, automotive backlite or back window, etc.) and other similar environments.

In certain embodiments, coating 3 and/or ta-C layer 7 may have an average hardness of from about 30-80 GPa (most preferably from about 40-75 GPa), and a bandgap of from about 1.8 to 2.2 eV. It is noted that the hardness and density of coating 3 and/or layers 7, 8 thereof may be adjusted by varying the ion energy of the depositing apparatus or process described below.

When substrate 1 of any of the aforesaid materials is coated with at least DLC coating 3 according to any of the Figs. 1-3 embodiments, the resulting coated article has the following characteristics in certain embodiments: visible transmittance (Ill. A) greater than about 60% (preferably greater than about 70%), UV (ultraviolet) transmittance less than about 38%, total solar transmittance less than about

45%, and IR (infrared) transmittance less than about 35% (preferably less than about 25%, and most preferably less than about 21%). Visible, "total solar", UV, and IR transmittance measuring techniques are set forth in Pat. No. 5 5,800,933, as well as the '008 patent, incorporated herein by reference.

Diamond-like carbon (DLC) and the special tetrahedral amorphous carbon (ta-C) form 7 of DLC utilized in certain embodiments herein will now be described in detail. All DLC 10 3 shown in drawings herein is amorphous. Ta-C 7 is amorphous and yet has substantial C-C tetrahedral (sp^3 -type) bonding and hence is termed tetrahedral amorphous carbon (ta-C) [or highly ta-C] as it has at least 35% sp^3 C-C bonds, preferably at least about 70% and most preferably at 15 least about 80% sp^3 C-C bonds. Diamond-like bonding gives this ta-C material gross physical properties approaching those of diamond such as high hardness, high density and chemical inertness. However, ta-C also includes sp^2 C-C trigonal bonding and its optical and electronic properties 20 are largely determined by this bonding component. The fraction of sp^2 bonding, and thus the density, in a ta-C layer depends for example on the carbon ion energy used

during deposition of coating 3 and/or layers 7 and 8.

Properties of a given DLC coating are a function of the
~~fraction of sp^3 to sp^2 bonding throughout the coating and~~
thus throughout layers 7 and 8.

5 It is noted that the sp^3 bonds discussed herein are sp^3
carbon-carbon bonds which result in a high density coating 3
and/or 7 and are not sp^3 carbon-hydrogen bonds which do not
provide as high of density.

 Depending on the technique of deposition, many ta-C
10 layers 7 herein contain amounts of H (up to about 4%) which
 either include the C atom to take either a tetrahedral
 configuration or an sp^2 planar configuration or to be sp -
 hybridised within a linear polymeric-like form. In other
 words C-C, C-H and H-H correlations all contribute to the
15 average structure of layers 7 in some embodiments.

 In the case of ta-C which is fully or at least about
 90% hydrogen-free, C-C bonding describes the local
 structure. Ta-C films also have some fraction of sp^2 or
 graphic bonding. The spatial distribution of trigonal (sp^2)
20 and tetrahedral carbon atoms may determine the bonding
 strength of layer(s) 3 to glass, as well as the layer's
 density, strength, stress, etc. Tetrahedral amorphous

carbon (ta-C) and its hydrogenated form ta-C:H (which contains no more than about 10 at% or so H) have the highest percentage of carbon-carbon (C-C) sp^3 bonding, and are used as layer 7 in the Fig. 1 embodiment and coating 3 in the Fig. 2 embodiment, and either of these in the Fig. 3 embodiment. This diamond-like bonding confers upon ta-C 7 properties which are unrivaled by other forms of so called DLC which have lower densities and/or greater proportion of graphitic sp^2 and polymeric sp C-C and C-H bonding.

10 Ta-C 7 has high density (at least about 2.4 grams per cubic centimeter), hardness, Young's modulus (700 - 800), as well as a low coefficient of friction (see Table 1 below).

TABLE 1

Properties	c-Diamond	ta-C	ta-C:H (10% at H)
Bandgap (eV)	5.45	2.0	2.2 - 2.5
Breakdown voltage (V cm ⁻¹) 10 ⁵	100	25 - 35	30
Dielectric Constant	5.5	4.5	4.7
Resistivity (ohm - cm)	10 ¹⁸	10 ¹¹	10 ¹²
Thermal Conductivity (Wcm ⁻¹ K ⁻¹)	20	0.1	0.1
Young's modulus Gpa	1000	700 - 800	500
Hardness (Gpa)	100	30 - 80	5 - 80
Refractive index	2.4	2.0	1.6 - 1.9
Structure	crystalline	amorphous	amorphous
Deposition condition/rate	high temp CVD 0.1 um/hr	low temp <200C 20A/s	low temp
wetability		contact angle 5 to 50	
Max thickness	> 1 um	<200 nm stress limited	<200 nm
Coefficient of Friction	<0.2 single crystal	<0.1	<0.1

Methods of depositing coating 3 on substrate 1 are
described below for certain embodiments of this invention.

Prior to coating 3 being formed on the glass substrate,
the top surface of substrate 1 is preferably cleaned by way
of an ion beam utilizing oxygen gas in each of the Fig. 1
and 2 embodiments. Oxygen gas physically cleans the surface

due to its atomic weight of from about 28 - 40 amu, most preferably about 32. Substrate 1 may also be cleaned by, for example, sputter cleaning the substrate prior to actual deposition of ta-C or other DLC material. This cleaning may
5 utilize oxygen and/or carbon atoms, and can be at an ion energy of from about 800 to 1200 eV, most preferably about 1,000 eV.

In plasma ion beam embodiments for depositing coatings 3, 7 and/or 8, carbon ions may be energized to form a stream
10 from plasma toward substrate 1 so that carbon from the ions is deposited on substrate 1. An ion beam from gas phase produces a beam of C⁺, CH⁺, C₂H⁺, and/or C₂H₂⁺ ions (i.e. carbon or carbon based radicals). Preferably, acetylene feedstock gas (C₂H₂) is used to prevent or minimize
15 polymerization and to obtain an appropriate energy to allow the ions to penetrate the substrate 1 surface and subimplant therein, thereby causing coating 3 atoms to intermix with the surface of substrate 1 a few atom layers thereinto. Impact energy of ions for the bulk of coating 3 (e.g. layer
20 7 in the Fig. 1 and 2 embodiments) may be from about 100 to 200 eV per carbon atom, preferably from about 100-150 eV, to cause dense sp³ C-C bonds to form in the DLC layer. The

ions impact the substrate with this energy which promotes formation of sp^3 carbon-carbon bonds. The impact energy of the energetic carbon ions may be within a range to promote formation of the desired lattice structure, such bonds in an interfacing portion (e.g. layer 8 in the Fig. 1 embodiment) of coating 3 apparently being formed at least in part by subimplantation into the substrate as shown in Figure 7. The stream may be optionally composed of ions having approximately uniform weight, so that impact energy will be approximately uniform. Effectively, the energetic ions impact on the growing film surface and/or substrate 1 and are driven into the growing film and/or substrate 1 to cause densification. Coating 3, and especially layer 7, are preferably free of pinholes, to achieve satisfactory water repulsion and suppression of soda diffusion.

Thus, the C-C sp^3 bonding is preferably formed by having a predetermined range of ion energy prior to reaching substrate 1, or prior to reaching ta-C growing on the substrate. The optimal ion energy window for ta-C layer 7 formation in the Fig. 1 and 2 embodiments is from about 100-200 eV (preferably from about 100-150 eV, and most preferably from about 100-140 eV) per carbon ion. At these

energies, films 7 (i.e. layer 3 in the Fig. 2 embodiment) emulate diamond.

~~However, compressive stresses can develop in ta-C when~~
being deposited at 100-150 eV. Such stress can reach as
5 high as 10 Gpa and can potentially cause delamination from
many substrates. It has been found that these stresses can
be controlled and decreased by increasing the ion energy the
deposition process to a range of from about 200-1,000 eV.
The plasma ion beam source enables ion energy to be
10 controlled within different ranges in an industrial process
for large area deposition utilized herein. The compressive
stress in amorphous carbon is thus decreased significantly
at this higher ion energy range of 200-1,000 eV.


High stress is undesirable in the thin interfacing
15 portion 8 of coating 3 that directly contacts the surface of
a glass substrate 1. Thus, for example, the first 1-40%
thickness (preferably the first 1-20% and most preferably
the first 5-10% thickness) 8 of coating 3 is deposited on
substrate 1 using high anti-stress energy levels of from
20 about 200-1,000 eV, preferably from about 400-500 eV. Then,
after this initial interfacing portion 8 of coating 3 has
been grown, the ion energy in the ion deposition process is

decreased (either quickly or gradually while deposition continues) to about 100-200 eV, preferably from about 100-150 eV, to grow the remainder ta-C layer 7 of coating 3.

For example, assume for exemplary purposes only with reference to Fig. 1 that DLC coating 3 is 100 Å thick. The first 10 Å layer 8 of coating 3 (i.e. interfacing portion 8) may be deposited using an ion energy of from about 400 to 500 eV so that layer 8 of coating 3 that contacts the surface of substrate 1 has reduced compressive stresses relative to the remainder 7 of coating 3. Interfacing portion 8 of coating 3 at least partially subimplants into the surface of substrate 1 to allow intermixing with the glass surface. In certain embodiments, only C ions are used in the deposition of interfacing layer 8, with the graded composition interface being mainly SiC. This interface 8 between substrate 1 and coating 3 improves adhesion of coating 3 to substrate 1 and the gradual composition change distributes strain in the interfacial region instead of narrowly concentrating it. Layer 8 of DLC coating 3 may or may not have a density of at least about 2.4 grams per cubic centimeter in different embodiments, and may or may not have at least about 35%, 70%, or 80% sp³ carbon-carbon bonds in

different embodiments. After the first 10 Å (i.e. layer 8) of coating 3 has been deposited, then the ion energy is ~~gradually or quickly decreased to 100 to 150 eV for the~~ remainder [may be either ta-C or ta-C:H] 7 of coating 3 so
5 that layer 7 has a higher density and a higher percentage of sp^3 C-C bonds than layer 8.

Thus, in certain embodiments, because of the adjustment in ion energy during the deposition process, ta-C coating 3 in Figs. 1-3 has different densities and different
10 percentages of sp^3 C-C bonds at different areas therein. However, at least a portion of coating 3 is a highly tetrahedral ta-C layer 7 having a density of at least about 2.4 grams per cubic centimeter and at least about 35% sp^3 . The highly tetrahedral ta-C portion is the portion furthest
15 from substrate 1 in Figure 1, but may optionally be at other areas of coating 3. In a similar manner, the portion of coating 3 having a lesser percentage of sp^3 C-C bonds is preferably the portion immediately adjacent substrate 1 (e.g. interfacing layer 8).

20 In certain embodiments, CH_4 may be used as a feedstock gas during the deposition process instead of or in combination with the aforesaid C_2H_2 gas. 

Referring to Figure 8, it is noted that the surface of a glass substrate has tiny cracks or microcracks defined therein. ~~These cracks may weaken glass by orders of~~ magnitude, especially when water seeps therein and ruptures further bonds. Thus, another advantage of this invention is that in certain embodiments amorphous carbon atoms and/or networks of layer 7 or 8 fill in or collect in these small cracks because of the small size of carbon atoms (e.g. less than about 100 pm radius atomic, most preferably less than about 80 pm, and most preferably about 76.7 pm) and because of the ion energy of 200 to 1,000 eV, preferably about 400-500 eV, and momentum. This increases the mechanical strength of the glass. The nano cracks in the glass surface shown in Figure 8 may sometimes be from about 0.4 nm to 1 nm in width. The inert nature and size of the carbon atoms in these nonocracks will prevent water from attacking bonds at the crack tip 14 and weakening the glass. The carbon atoms make their way to positions adjacent the tips 14 of these cracks, due to their size and energy. Tips 14 of these cracks are, typically, from about 0.5 to 50 nm below the glass substrate surface. The top surface of layers 7 and/or

8 remains smooth and/or approximately flat within about less than 1.0 nm even above the cracks.

~~Carbon is now described generally, in many of its~~
forms, to aid in the understanding of this invention.

5 Carbon has the ability to form structures based on directed covalent bonds in all three spatial dimensions. Two out of the six electrons of a carbon atom lie in the 1s core and hence do not participate in bonding, while the four remaining 2s and 2p electrons take part in chemical bonding
10 to neighboring atoms. The carbon atom's one 2s and three 2p electron orbitals can hybridise in three different ways. This enables carbon to exist as several allotropes. In nature, three allotropic crystalline phase exists, namely diamond, graphite and the fullerenes and a plethora of non-
15 crystalline forms.

For the diamond crystalline allotrope, in tetrahedral or sp^3 bonding all the four bonding electrons form σ bonds. The space lattice in diamond is shown in Figure 4 where each carbon atom is tetrahedrally bonded to four other carbon
20 atoms by σ bonds of length 0.154 nm and bond angle of $109^\circ 53''$. The strength of such a bond coupled with the fact that diamond is a macromolecule (with entirely covalent bonds)

give diamond unique physical properties: high atomic density, transparency, extreme hardness, exceptionally high thermal conductivity and extremely high electrical resistivity ($10^{16} \Omega\text{-cm}$).

5 The properties of graphite are governed by its trigonal bonding. The outer 2s, $2p_x$ and $2p_y$ orbitals hybridise in a manner to give three co-planar sp^2 orbitals which form σ bonds and a p-type π orbital $2p_z$ perpendicular to the sp^2 orbital plane, as shown in Figure 5. Graphite consists of
10 hexagonal layers separated from each other by a distance of 0.34 nm. Each carbon atom is bonded to three others by 0.142 nm long σ bonds within an hexagonal plane. These planes are held together by weak van der Waals bonding which explains why graphite is soft along the sp^2 plane.

15 As for fullerenes, it is known that C_{60} and C_{70} are the most accessible members of the family of closed-cage molecules called fullerenes, formed entirely of carbon in the sp^2 hybridised state. Each fullerenes C_n consists of 12 pentagonal rings and m hexagonal rings such that $m = (n -$
20 $20)/2$ (satisfying Euler's Theorem). The σ bonds are wrapped such that the fullerene has a highly strained structure and the molecule is rigid.

As for amorphous carbon, there exists a class of carbon in the metastable state without any long range order. ~~Material properties change when using different deposition~~ techniques or even by varying the deposition parameters within a single technique. In this category of materials on one extreme we have ta-C (e.g. layer 7) which is the most diamond-like with up to 90% C-C sp^3 bonding in certain preferred embodiments and on the other a-C (amorphous carbon), produced by thermal evaporation of carbon, in which more than 95% graphitic bonds are prevalent. In this respect, these two materials reflect the intrinsic diversity of non-crystalline forms of carbon.

Amorphous materials, such as layer(s) 3, 7 and 8, are metastable solids. In an amorphous solid there exists a set of equilibrium positions about which atoms oscillate. The atoms in an amorphous material are often extended into a three dimensional network with the absence of order beyond the second nearest neighbor distance.

Referring again to ta-C layer 7, the sp^3/sp^2 C-C bonded fraction or percentage (%), e.g. in a vacuum arc deposition technique or techniques used in the '477 patent or deposition techniques discussed above, can be controlled by

changing the energy of the incident C^+ ions. The films deposited being metastable in nature are under high compressive stress. ~~The sp^2 hybridised carbon atoms are~~ clustered and embedded within a sp^3 matrix. The extent of the latter bonding confers onto ta-C its diamond-like physical properties. The fraction of the sp^2 hybridised atoms determines the extent of clustering. The degree of clustering, which is seen as a strain relief mechanism, implies that the π and π^* states become delocalised to such an extent that they control the electronic and optical properties of the films. At high density of states, the π bands merge with the σ states to form the conduction and valence mobility band-edges. Their lower density tail states are localised giving a pseudo-gap. The term "tetrahedral amorphous carbon (ta-C)" is thus used to distinguish this highly tetrahedral material from other "diamond-like carbon" which have C-C correlations mostly of the sp^2 type.

The sp^3 bonding in coatings 3 is believed to arise from a densification process under energetic ion bombardment conditions. Hybridisation of the carbon atom is expected to adjust to the local density, becoming more sp^3 if the

density is high and more sp^2 if low. This can occur if an incident ion penetrates the first atomic layer and then ~~enters an interstitial subsurface position. The local~~ bonding then reforms around this atom and its neighbours to
5 adopt the most appropriate hybridisation. High energy ions in principle can penetrate the surface layer of the substrate or growing DLC, increase the density of deeper layers which then forces sp^3 bonding. Ions of lower energy than the penetration threshold only append to the surface
10 forming sp^2 bonded a-C.

Coated articles according to any of the aforesaid embodiments may be used, for example, in the context of automotive windshields, automotive back windows, automotive side windows, architectural glass, IG glass units,
15 residential or commercial windows, and the like.

In any of the aforesaid embodiments, a layer of non-porous tungsten disulfide (WS_2) 12 may be provided on top of layer 7 to prevent the DLC from burning off upon exposure to air if taken to high temperatures after the coating
20 deposition. Layer 12 (e.g. see Figure 8) may be applied by plasma spraying to a thickness of from about 300 to 10,000

Å. WS, layer 12 is removeable in certain embodiments.

Other suitable materials may instead be used for layer 12.

~~Once given the above disclosure, many other features,~~
modifications, and improvements will become apparent to the
5 skilled artisan. Such other features, modifications, and
improvements are, therefore, considered to be a part of this
invention, the scope of which is to be determined by the
following claims.

I CLAIM:

1 1. A coated glass comprising:
2 a soda inclusive glass substrate comprising, on a
3 weight basis:
4 SiO₂ from about 60-80%,
5 Na₂O from about 10-20%,
6 CaO from about 0-16%,
7 K₂O from about 0-10%,
8 MgO from about 0-10%,
9 Al₂O₃ from about 0-5%; and
10 a non-crystalline diamond-like carbon (DLC)
11 coating provided on said glass substrate, wherein said DLC
12 coating includes at least a first highly tetrahedral
13 amorphous carbon layer having at least about 35% sp³ carbon-
14 carbon bonds and an average density of at least about 2.4
15 gm/cm³.

1 2. The coated glass of claim 1, wherein said DLC
2 coating further includes a second layer therein of amorphous
3 carbon that is in direct contact with said substrate so that
4 said second layer is disposed between said substrate and
5 said first highly tetrahedral amorphous carbon layer, and

6 wherein said first highly tetrahedral amorphous carbon layer
7 has a greater density and a greater percentage of sp^3
8 ~~carbon-carbon bonds than said second layer of amorphous~~
9 carbon.

1 3. The coated glass of claim 1, wherein said first
2 highly tetrahedral amorphous carbon layer has at least about
3 70% sp^3 carbon-carbon bonds, and wherein said glass
4 substrate is a soda lime silica glass substrate including
5 from about 66-75% SiO_2 , from about 10-20% Na_2O , from about
6 5-15% CaO , from about 0-5% MgO , from about 0-5% Al_2O_3 , and
7 from about 0-5% K_2O .

1 4. The coated glass of claim 3, wherein said highly
2 tetrahedral amorphous carbon layer has at least about 80%
3 sp^3 carbon-carbon bonds.

1 5. The coated glass of claim 3, wherein said DLC
2 coating has an average hardness of at least about 40 Gpa,
3 and an average density of at least about 2.4 gm/cm³.

1 6. The coated glass of claim 1, wherein said DLC
2 coating has a thickness of from about 30 to 3,000 Å.

1 7. The coated glass of claim 6, wherein said DLC
2 coating has a thickness of from about 50 to 300 Å.

1 8. The coated glass of claim 1, wherein said DLC
2 coating has a bandgap of from about 1.8 to 2.2 eV.

1 9. The coated glass of claim 1, wherein the coated
2 glass comprises the following characteristics:

3 visible transmittance (Ill. A): > 60%

4 UV transmittance: < 38%

5 IR transmittance: < 35%.

1 10. The coated glass of claim 1, wherein said DLC
2 coating includes at least about 70% sp³ carbon-carbon bonds.

1 11. The coated glass of claim 1, wherein said DLC
2 coating includes at least about 80% sp³ carbon-carbon bonds.

1 12. The coated glass of claim 1, wherein said DLC
2 coating is from about 30 to 3,000 Å thick, and wherein said
3 ~~first highly tetrahedral amorphous carbon layer of said DLC~~
4 coating is from about 30 to 2,900 Å thick.

1 13. The coated glass of claim 1, wherein said DLC
2 coating includes sp^3 carbon-carbon bonds subimplanted in a
3 surface of said glass substrate so as to strongly bond said
4 DLC coating to said glass substrate.

1 14. The coated glass of claim 1, further comprising a
2 low-E coating system having at least one layer provided
3 between said glass substrate and said DLC layer.

1 15. A coated glass comprising:
2 a glass substrate including at least about 5% by
3 weight Na_2O ;
4 a highly tetrahedral amorphous carbon layer, for
5 reducing corrosion on the substrate, having a density of at
6 least about 2.4 gm/cm³ provided on said glass substrate in
7 order to reduce corrosion or stains on the coated glass,

8 wherein said highly tetrahedral amorphous carbon layer
9 includes sp^2 and sp^3 carbon-carbon bonds; and

10 ~~wherein said highly tetrahedral amorphous carbon~~
11 layer has more sp^3 carbon-carbon bonds than sp^2 carbon-
12 carbon bonds.

1 16. The coated glass of claim 15, further comprising
2 another amorphous carbon layer located between said
3 substrate and said highly tetrahedral amorphous carbon
4 layer, and wherein said another amorphous carbon layer has a
5 density less than said highly tetrahedral amorphous carbon
6 layer and a lesser percentage of sp^3 carbon-carbon bonds
7 than said highly tetrahedral amorphous carbon layer.

1 17. The coated glass of claim 15, wherein said highly
2 tetrahedral amorphous carbon layer has at least about 70%
3 sp^3 carbon-carbon bonds, and a thickness of from about 30-
4 300 Å.

1 18. The coated glass of claim 17, wherein said highly
2 tetrahedral amorphous carbon layer is in direct contact with
3 said glass substrate.

1 19. A coated glass comprising:

2 ~~a soda inclusive glass substrate comprising, on a~~
3 weight basis:

4 SiO₂ from about 60-80%,

5 Na₂O from about 10-20%,

6 CaO from about 0-16%,

7 K₂O from about 0-10%,

8 MgO from about 0-10%,

9 Al₂O₃ from about 0-5%;

10 a diamond-like carbon (DLC) coating provided on
11 said glass substrate for reducing visible corrosion, wherein
12 said DLC coating has an average density of at least about
13 2.4 gm/cm³ and a thickness of from about 50 to 300 Å; and

14 wherein the coated glass comprises the following
15 characteristics:

16 visible transmittance: > 60%

17 UV transmittance: < 38%

18 IR transmittance: < 35%.

1 20. A method of making a coated glass article, the
2 method comprising the steps of:

3 providing a glass substrate comprising, on a
4 weight basis, 60-80% SiO_2 , 10-20% Na_2O , 0-16% CaO , 0-10% K_2O ,
5 ~~0-10% MgO , and 0-5% Al_2O_3 , and~~
6 forming at least one highly tetrahedral amorphous
7 carbon layer having more sp^3 carbon-carbon bonds than sp^2
8 carbon-carbon bonds on the glass substrate for reducing
9 potential for corrosion.

1 21. The method of claim 20, wherein said forming step
2 includes using a plasma ion beam and using acetylene gas to
3 form the at least one carbon layer on the glass substrate.

1 22. The method of claim 20, wherein said forming step
2 includes using a plasma ion beam to form the highly
3 tetrahedral amorphous carbon layer, and varying the ion
4 energy from about 200 to 800 eV during the deposition of an
5 interfacial portion of the amorphous carbon layer deposited
6 immediately adjacent the substrate to a lower level of from
7 about 100 to 150 eV during the deposition of a higher
8 density portion of the carbon layer that is deposited over
9 the interfacial portion.

1 23. An automotive window comprising:
2 a substrate transparent to at least about 70% of
3 ~~visible light rays;~~
4 a highly tetrahedral amorphous carbon inclusive
5 coating provided on said substrate, wherein said coating has
6 a thickness of from about 50 to 300 Å and a substantial
7 number of sp³ carbon-carbon bonds; and
8 wherein the automotive window comprises the
9 following optical characteristics:
10 visible transmittance: > 70%
11 UV transmittance: < 38%
12 IR transmittance: < 35%.

1 24. The automotive window of claim 23, wherein said
2 substrate includes one of soda lime silica glass,
3 borosilicate glass, and substantially transparent plastic,
4 and wherein said coating has an average density of at least
5 about 2.4 gm/cm³.

1 25. The automotive window of claim 23, wherein the
2 window is an automotive windshield.

1 26. A method of coating a glass substrate to improve
2 long-term strength of the glass substrate, the method
3 ~~comprising the steps of:~~

4 providing a glass substrate having at least one
5 crack with a tip defined therein;

6 depositing a layer of diamond-like carbon directly
7 on the glass substrate at an energy level so that carbon
8 atoms make their way into the crack to a location proximate
9 the tip of the crack; and

10 the carbon atoms in the crack preventing some
11 water molecules from reaching a silicon-oxygen bond at the
12 tip of the crack thereby improving the long-term strength of
13 the glass.

1 27. The method of claim 26, wherein said energy level
2 is an ion energy level of from about 200 to 1,000 eV.

AMENDED CLAIMS

[received by the International Bureau on 24 November 2000 (24.11.00);
original claims 26 and 27 cancelled; remaining claims unchanged (1 page)]

7

1/4




FIG. 1




FIG. 2




FIG. 3

2/4




FIG. 4




FIG. 5




FIG. 6

3/4




FIG. 7




FIG. 8

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 00/11711

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 C03C17/22 C03C17/34 C03C23/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C03C C23C G11B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, INSPEC, WPI Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	"SURFACE HARDENING OF CERAMIC AND GLASS MATERIALS" IBM TECHNICAL DISCLOSURE BULLETIN, US, IBM CORP. NEW YORK, vol. 36, no. 3, 1 March 1993 (1993-03-01), page 291 XP000354780 ISSN: 0018-8689 the whole document	1-27
X	"SURFACE HARDENING OF CERAMIC AND GLASS MATERIALS" IBM TECHNICAL DISCLOSURE BULLETIN, US, IBM CORP. NEW YORK, vol. 36, no. 1, 1993, page 225 XP000333837 ISSN: 0018-8689 the whole document	1-27
	-/-	



Further documents are listed in the continuation of box C.



Patent family members are listed in annex.

* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

20 September 2000

Date of mailing of the international search report

29/09/2000

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Somann, K

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 00/11711

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	VEERASAMY V S ET AL: "OPTICAL AND ELECTRONIC PROPERTIES OF AMORPHOUS DIAMOND" DIAMOND AND RELATED MATERIALS, NL, ELSEVIER SCIENCE PUBLISHERS, AMSTERDAM, vol. 2, no. 5/07, 13 April 1993 (1993-04-13), pages 782-787, XP000414263 ISSN: 0925-9635 the whole document	1-27
X	WO 97 45834 A (WEILER MANFRED ; AKASHIC MEMORIES CORP (US); VEERASAMY VIJAYEN (US)) 4 December 1997 (1997-12-04) page 5, line 18 - page 7, line 31 page 8, line 13 - line 24 page 11, line 19 page 12, line 3 - page 14, line 27 page 32, line 37 - page 35, line 35	1-27
X	WO 98 45847 A (GERSTNER EDMUND GLENN ; UNIV SYDNEY (AU)) 15 October 1998 (1998-10-15) the whole document page 7, line 19 - line 20	1-27
X	WO 94 12680 A (AMARATUNGA GEHAN ANIL JOSEPH ; MCKENZIE DAVID ROBERT (AU)) 9 June 1994 (1994-06-09) page 1, line 4 - page 2, line 8 page 2, line 19 - line 25 page 8, line 24 - line 35 page 12, line 14 - line 29	1-27
X	US 5 527 596 A (KIMOCK FRED M ET AL) 18 June 1996 (1996-06-18) the whole document	1-27
A	WEILER M ET AL: "PREPARATION AND PROPERTIES OF HIGHLY TETRAHEDRAL HYDROGENATED AMORPHOUS CARBON" PHYSICAL REVIEW, US, AMERICAN INSTITUTE OF PHYSICS. NEW YORK, vol. 53, no. 3, 15 January 1996 (1996-01-15), pages 1594-1607, XP002041955 the whole document	1-27

-/-

INTERNATIONAL SEARCH REPORT

International Application No
PCT/US 00/11711

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	VEERASAMY V S ET AL: "ELECTRONIC DENSITY OF STATES IN HIGHLY TETRAHEDRAL AMORPHOUS CARBON" SOLID STATE ELECTRONICS, GB, ELSEVIER SCIENCE PUBLISHERS, BARKING, vol. 37, no. 2, 1994, pages 319-326, XP002041954 ISSN: 0038-1101 the whole document	1-27
A	WEILER M ET AL: "HIGHLY TETRAHEDRAL, DIAMOND-LIKE AMORPHOUS HYDROGENATED CARBON PREPARED FROM A PLASMA BEAM SOURCE" APPLIED PHYSICS LETTERS, US, AMERICAN INSTITUTE OF PHYSICS. NEW YORK, vol. 64, no. 21, 23 May 1994 (1994-05-23), pages 2797-2799, XP000449616 ISSN: 0003-6951 the whole document	1-27
A	KUHN M ET AL: "DEPOSITION OF CARBON FILMS BY A FILTERED CATHODIC ARC" DIAMOND AND RELATED MATERIALS, NL, ELSEVIER SCIENCE PUBLISHERS, AMSTERDAM, vol. 2, no. 10, 16 August 1993 (1993-08-16), pages 1350-1354, XP000413562 ISSN: 0925-9635 the whole document	1-27
A	"CHEMICAL ABSTRACTS + INDEXES, US, AMERICAN CHEMICAL SOCIETY. COLUMBUS" CHEMICAL ABSTRACTS + INDEXES, US, AMERICAN CHEMICAL SOCIETY. COLUMBUS, XP000660696 ISSN: 0009-2258 the whole document	1-27

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 00/11711

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 9745834 A	04-12-1997	US 5858477 A AU 3224297 A AU 3293097 A EP 0906636 A EP 0909445 A WO 9745855 A	12-01-1999 05-01-1998 05-01-1998 07-04-1999 21-04-1999 04-12-1997
WO 9845847 A	15-10-1998	AU 6813698 A	30-10-1998
WO 9412680 A	09-06-1994	AU 5532194 A	22-06-1994
US 5527596 A	18-06-1996	US 5135808 A US 5268217 A CA 2172829 A EP 0728069 A WO 9513189 A US 5508092 A US 5635245 A US 5844225 A AT 190005 T CA 2090109 A DE 69132010 D EP 0550630 A JP 6501745 T WO 9205951 A US 5643423 A US 5506038 A US 5637353 A CA 2141536 A EP 0652828 A JP 8500063 T WO 9403331 A	04-08-1992 07-12-1993 18-05-1995 28-08-1996 18-05-1995 16-04-1996 03-06-1997 01-12-1998 15-03-2000 28-03-1992 06-04-2000 14-07-1993 24-02-1994 16-04-1992 01-07-1997 09-04-1996 10-06-1997 17-02-1994 17-05-1995 09-01-1996 17-02-1994